

ASP 7600 Conductive Bags

ASP 7600-M CONDUCTIVE BAGS TYPICAL PROPERTIES			
	Value	Unit	Test Method
ELECTRICAL PROPERTIES			
Static Decay Test <i>(From 5000V to 1% at 73°F, 12% RH)</i>	less than 0.01	seconds	Method 4046*
Volume Resistivity	2×10^4	ohm-cm	ASTM D 257
Surface Resistivity	1×10^4	ohm/sq.	ASTM D 257
PHYSICAL PROPERTIES			
Tensile strength at break (TD)	12.1	MPa	ISO-R-1184
Tensile strength at break (MD)	11.5	MPa	ISO-R-1184
Elongation at break (TD)	270	MPa	ISO-R-1184
Elongation at break (MD)	300	MPa	ISO-R-1184

*Federal Test Method Standard 101B, per Mil-B-81705C