

## ASP 5600-M Antistatic Transparent Pink Polyethylene Bags

<b>ASP 5600-M ANTISTATIC TRANSPARENT PINK POLYETHYLENE BAGS TYPICAL PROPERTIES</b>				
		Value	Unit	Test Method
	<b>ELECTRICAL PROPERTIES</b>			
	Static Decay Test (From 5000V to 1% at 73°F, 12% RH)	less than 2	seconds	Method 4046*
	Surface Resistivity	$10^{10}$	ohm/sq	ASTM D 257
	<b>PHYSICAL PROPERTIES</b>			
Strength	Tensile	185	kg/cm2	ASTM D 882
	Tear	1200	grams	ASTM D 1922
Water Absorbtion	(24 hours)	0.01	%	ASTM D 570
Heat Seal	Temperature	82 to 121	°C	
	Time	0.5 to 5	seconds	
Temperature Range	Maximum	93	°C	
	Minimum	-15	°C	

\*Federal Test Method Standard 101B, per Mil-B-81705C